

Tableau comparatif des coefficients d'absorption alpha

GRAMITHERM[®]
Grass Insulating Swiss Technology



Fréquence	Gramitherm	Mélamine	Laine verre
Hz	Coefficient α		
200	0,26	0,18	0,16
250	0,34	0,25	0,25
315	0,46	0,32	0,34
400	0,59	0,38	0,45
500	0,73	0,5	0,59
630	0,87	0,71	0,71
800	0,96	0,82	0,86
1000	0,99	0,93	0,94
1250	0,95	0,98	1
1600	0,92	1	1



