

Page 1/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

SECTION 1: Identification of the substance/mixture and of the company/ undertaking

· 1.1 Product identifier

- Trade name: KEIM INNOSTAR
- 1.2 Relevant identified uses of the substance or mixture and uses advised against
- Application of the substance / the mixture Sol-silicate paint for interior use.
- · Uses advised against All other uses are not recommended.

• 1.3 Details of the supplier of the safety data sheet

• Manufacturer/Supplier: KEIMFARBEN GMBH Keimstraße 16 / 86438 Diedorf Tel. +49 (0)821 4802-0 Fax +49 (0)821 4802-210 www.keimfarben.de / info@keimfarben.de

- Further information obtainable from: Product safety department Telefon: 49(0)821/4802-138 E-Mail: sdb.info@keimfarben.de
- **1.4 Emergency telephone number:** GBK GmbH Global Regulatory Compliance Emergency number: +49(0)6132/84463

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

· Classification according to Regulation (EC) No 1272/2008

The product is not classified according to the CLP regulation.

- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008 Void
- · Hazard pictograms Void
- · Signal word Void
- · Hazard statements Void
- 2.3 Other hazards Alkaline product. Avoid contact with skin and eyes.
- Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description: Aqueous solution of amorphous silica, organically modified, fillers and pigments.
- · Dangerous components: Void

(Contd. on page 2)

DEN



Page 2/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

Trade name: KEIM INNOSTAR

(Contd. of page 1)

SECTION 4: First aid measures · 4.1 Description of first aid measures · General information: No special measures required. When seeing the doctor we suggest to present this safety data sheet. · After inhalation: Supply fresh air; consult doctor in case of complaints. · After skin contact: Immediately wash with water and soap and rinse thoroughly. Do not use solvents or thinners. If skin irritation continues, consult a doctor. · After eye contact: Rinse opened eye for several minutes under running water. Then consult a doctor. After swallowing: Rinse mouth and throat well with water. Do not induce vomiting; call for medical help immediately. 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available. • 4.3 Indication of any immediate medical attention and special treatment needed No further relevant information available. **SECTION 5: Firefighting measures** 5.1 Extinguishing media · Suitable extinguishing agents: Product itself does not burn. Co-ordinate fire-fighting measures to the fire surroundings. 5.2 Special hazards arising from the substance or mixture No further relevant information available. · 5.3 Advice for firefighters · Protective equipment: Wear self-contained respiratory protective device. · Additional information Cool endangered receptacles with water spray. Dispose of fire debris and contaminated fire fighting water in accordance with official regulations. In case of fire do not breathe smoke, fumes and vapours. **SECTION 6: Accidental release measures** · 6.1 Personal precautions, protective equipment and emergency procedures

Ensure adequate ventilation Avoid contact with skin and eyes. Particular danger of slipping on leaked/spilled product. Respect the protection rules (see section 7 a. 8). • 6.2 Environmental precautions:

Do not allow product to reach soil, sewage system or any water course. Follow local governmental rules and regulations.

(Contd. on page 3)

⁻ DEN



Page 3/8


Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

Trade name: KEIM INNOSTAR



Ingredients with limit values that require monitoring at the workplace: alveoles penetrating component

14808-60-7 Quartz (SiO2)

MAK (Germany) alveolengängige Fraktion

• Additional information: The lists valid during the making were used as basis.

(Contd. on page 4)

⁻ DEN



Page 4/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

Trade name: KEIM INNOSTAR

Personal protective and hygienic measures: Avoid contact with the eyes and skin. Do not inhale aerosols. Wash hands before breaks and at the end of work. Immediately remove all soiled and contaminated clothing Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of uality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The vexct break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Therefore a maximum wearing time, which corresponds to 50% of the p		(Contd. of page
General protective and hygienic measures: Avoid contact with the eyes and skin. Do not inhale aerosols. Wash hands before breaks and at the end of work. Immediately remove all solied and contaminated clothing Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,7 mm The selection of the application. Pertextent of glove manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. Eye protection: Eye protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. </th <th>8.2 Exposure controls</th> <th></th>	8.2 Exposure controls	
Avoid contract with the eyes and skin. Do not inhale aerosols. Wash hands before breaks and at the end of work. Immediately remove all soiled and contaminated clothing Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile imprenated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile inprenated cotton-gloves Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to the capplication. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Section o		
Do not inhale aerosols. [•] Wash hands before breaks and at the end of work. Immediately remove all solied and contaminated clothing Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves Suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Buty rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves are on any depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practit conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. Fye protection: Fye protection: Fye protection: Fyentetion: Fyentetio		
Wash hands before breaks and at the end of work. Immediately remove all solied and contaminated clothing Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile inuber, NBR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practition of the sole beaved. Perepretion: Tighty sealed goggles Body protection: Protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Second protection: Protection: Protection: <		ıd skin.
Immediately remove all soiled and contaminated clothing Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butly rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mai of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practit conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. Fye protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Form: Pasty Colour: Odourless Odour threshold: Not determined. PH-value: Alkaline		
Respiratory protection: Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further main of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum waring time, which corresponds to 50% of the penetration time is recommended. Step protection: Tighty sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Step protection: Papearance: Form: Pasty		
Use suitable respiratory protective device only when aerosol or mist is formed. Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Odour: Odouriess Odour threshold: Not determined. PH-value: Alkaline		and contaminated clothing
Filter: P2 Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butly rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practit conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Odourless Odour threshold: Not determined. PH-value: Alkaline		ative device only when acrossl or mist is formed
Protection of hands: Protective gloves Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Section on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to co		sive device only when acrosol of this is formed.
Material of gloves suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nutrile rubber, NBR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SeccrION 9: Physical and chemical properties General Information Appearance: Parmi		ive aloves
suitable material e.g.: Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Odourless Odour threshold: Not determined. PH-value: Alkaline		
Nitrile impregnated cotton-gloves Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. Section on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odou		
Recommended thickness of the material: ≥ 0,5 mm Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further marging of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odourless Odourless Odour threshold: Not determined. <td></td> <td>/es</td>		/es
Nitrile rubber, NBR Recommended thickness of the material: ≥ 0,4 mm Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odourless Odourless Odour threshold: Not determined.		
Butyl rubber, BR Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mai of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tim is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Thet work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Form: Form: Colour: Different, according to colouring. Odour threshold: Not determined. PH-value: Alkaline		
Recommended thickness of the material: ≥ 0,7 mm The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Protection: Protection: Protection: Protection: SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined.		ne material: \geq 0,4 mm
The selection of the suitable gloves does not only depend on the material, but also on further main of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Odouries Odouries Odouries Odouries Odour threshold: Not determined. PH-value: Alkaline		
of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Odouries Odouries Odouries Odouries Not determined. pH-value: Alkaline		
substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Odour: Odour: Odour threshold: PH-value: Alkaline		
to be checked prior to the application. Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration times is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Pasty Colour: Odour: Odour: Odour: Ph-value: Alkaline		
Penetration time of glove material Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odourless Odourless Odour threshold: Not determined.		
Value for the permeation: Level ≥ 6 (480 min) The determined penetration times according to EN 374 part III are not performed under practic conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline		
The determined penetration times according to EN 374 part III are not performed under practice conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration time is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Colour: Odour: Odourless Odour threshold: Not determined.		
conditions. Therefore a maximum wearing time, which corresponds to 50% of the penetration tin is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Form: Colour: Odouri: Odourless Odour threshold: PH-value: Alkaline		
is recommended. The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Colour: Odour: Odour: Odouress Odour threshold: PH-value: Alkaline		
The exact break trough time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information Appearance: Form: Form: Colour: Different, according to colouring. Odour threshold: Not determined. PH-value: Alkaline		full wearing time, which corresponds to 50% of the period ation tim
has to be observed. Eye protection: Tightly sealed goggles Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties 9.1 Information Appearance: Form: Form: Pasty Colour: Different, according to colouring. Odour: Odour threshold: Not determined. pH-value: Alkaline		has to be found out by the manufacturer of the protective gloves a
Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline		
Body protection: Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline	• Eye protection: Tightly sealed	d goggles
Protective work clothing After contact with skin wash thoroughly with water and apply lotion. SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour threshold: Not determined. PH-value: Alkaline		
SECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline		
9.1 Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline	After contact with skin wash th	oroughly with water and apply lotion.
9.1 Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline		
9.1 Information on basic physical and chemical properties General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline	SECTION 9: Physical ar	nd chemical properties
General Information Appearance: Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline		
Appearance: Pasty Form: Pasty Colour: Different, according to colouring. Odour: Odourless Odour threshold: Not determined. pH-value: Alkaline		isical and chemical properties
Form:PastyColour:Different, according to colouring.Odour:OdourlessOdour threshold:Not determined.PH-value:Alkaline		
Colour:Different, according to colouring.Odour:OdourlessOdour threshold:Not determined.PH-value:Alkaline		Pastv
Odour: Odourless Odour threshold: Not determined. PH-value: Alkaline	-	,
Odour threshold: Not determined. pH-value: Alkaline	· Odour:	
PH-value: Alkaline	· Odour threshold:	
		(Contd. on page



Page 5/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

Trade name: KEIM INNOSTAR

	(Contd. of page 4
 Change in condition Melting point/Melting range: Boiling point/Boiling range: 	Undetermined. >100 °C
· Flash point:	Not applicable.
Flammability (solid, gaseous):	Not applicable.
Ignition temperature:	Not determined.
Decomposition temperature:	Not determined.
Self-igniting:	Product is not selfigniting.
Danger of explosion:	Product does not present an explosion hazard.
 Explosion limits: Lower: Upper: Oxidising properties 	Not applicable. Not applicable. Not applicable.
· Vapour pressure at 20 °C:	~23 hPa
Density at 20 °C: Relative density Vapour density Evaporation rate	1,55* g/cm ³ Not determined. Not applicable. Not applicable.
 Solubility in / Miscibility with water: 	Fully miscible.
· Partition coefficient (n-octanol/wa	ter): Not applicable.
 Viscosity: Dynamic at 20 °C: Kinematic: 9.2 Other information 	3000-4500* mPas Not determined. * The values are for freshly produced material and may change with the time.

SECTION 10: Stability and reactivity

• **10.1 Reactivity** No further relevant information available.

• **10.2 Chemical stability** Stable under normal conditions of storage and use. • **Thermal decomposition / conditions to be avoided:**

- No decomposition if used according to specifications.
- 10.3 Possibility of hazardous reactions No dangerous reactions known.
- 10.4 Conditions to avoid No further relevant information available.
- · 10.5 Incompatible materials: Acids

(Contd. on page 6)

- DEN



Page 6/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

(Contd. of page 5)

Trade name: KEIM INNOSTAR

· 10.6 Hazardous decomposition products:

No hazardous decomposition products if stored and handled as prescribed.

SECTION 11: Toxicological information

- · 11.1 Information on toxicological effects
- Acute toxicity Based on available data, the classification criteria are not met.
- Primary irritant effect:
- · Skin corrosion/irritation Frequent persistent contact with the skin may cause skin irritation.
- Serious eye damage/irritation In case of longer exposure, irritating effect is possible.
- · during inhalation: Irritant effect possible.
- during swallowing: Irritant effect possible
- Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- Other information (about experimental toxicology):
- Experimental analysis are not available.

The product was not tested. The statements on toxicology have been derived from the properties of the individual components.

- · CMR effects (carcinogenity, mutagenicity and toxicity for reproduction) not applicable
- · Germ cell mutagenicity Based on available data, the classification criteria are not met.
- · Carcinogenicity Based on available data, the classification criteria are not met.
- **Reproductive toxicity** Based on available data, the classification criteria are not met.
- \cdot STOT-single exposure Based on available data, the classification criteria are not met.
- \cdot STOT-repeated exposure Based on available data, the classification criteria are not met.
- · Aspiration hazard Based on available data, the classification criteria are not met.

SECTION 12: Ecological information

- · 12.1 Toxicity
- Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- **12.4 Mobility in soil** No further relevant information available.
- Additional ecological information:
- AOX-indication:

Due to the substance of content which do not include organic jointed halogens, the product can not take influence on the AOX-load of the waste water.

According to the formulation contains the following heavy metals and compounds from the EU guideline NO. 2006/11/EC:

The product contains TiO2.

General notes:

At present there are no ecotoxicological assessments.

Water hazard class 1 (German Regulation) (Self-assessment): slightly hazardous for water Do not allow product to reach ground water, water course or sewage system.

- 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- **vPvB:** Not applicable.

(Contd. on page 7)

⁻ DEN



Page 7/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

Trade name: KEIM INNOSTAR

· 12.6 Other adverse effects No further relevant information available.

(Contd. of page 6)

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

Recommendation

Must not be disposed with household garbage. Do not allow product to reach sewage system. Disposal must be made according to official regulations.

· European waste catalogue

08 01 12 waste paint and varnish other than those mentioned in 08 01 11

· Uncleaned packaging:

• **Recommendation:** Disposal must be made according to official regulations.

• Recommended cleansing agents: Water, if necessary with cleansing agents.

SECTION 14: Transport informa	ition
· 14.1 UN-Number · ADR, IMDG, IATA	Void
 14.2 UN proper shipping name ADR, IMDG, IATA 	Void
· 14.3 Transport hazard class(es)	
· ADR, IMDG, IATA · Class	Void
· 14.4 Packing group · ADR, IMDG, IATA	Void
 14.5 Environmental hazards: Marine pollutant: 	No
· 14.6 Special precautions for user	Not applicable.
 14.7 Transport in bulk according to Ar of Marpol and the IBC Code 	nnex II Not applicable.
· Transport/Additional information:	No dangerous good in sense of these transpor regulations.
· UN "Model Regulation":	Void

(Contd. on page 8)



Page 8/8

Safety data sheet according to 1907/2006/EC, Article 31

Printing date 28.07.2016

Version number 2

Revision: 28.07.2016

Trade name: KEIM INNOSTAR

(Contd. of page 7)

SECTION 15: Regulatory information

- 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- National regulations:
- · Waterhazard class: Water hazard class 1 (Self-assessment): slightly hazardous for water.
- · Other regulations, limitations and prohibitive regulations
- Substances of very high concern (SVHC) according to REACH, Article 57 not applicable • Product-Code/Giscode: M-SK01
- 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Department issuing SDS: KEIMFARBEN Germany, Product safety department

Abbreviations and acronyms:

ADR: Accord européen sur le transport des marchandises dangereuses par Route (European Agreement concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) TRGS: Technische Regeln für Gefahrstoffe (Technical Rules for Dangerous Substances, BAuA, Germany) VOC: Volatile Organic Compounds (USA, EU) PBT: Persistent, Bioaccumulative and Toxic SVHC: Substances of Very High Concern vPvB: very Persistent and very Bioaccumulative AGW: Arbeitsplatzgrenzwert (Germany) REACH: Registration, Evaluation and Authorisation of Chemicals (Regulation (EC) No.1907/2006) * * Data compared to the previous version altered.

DEN